

LANDECOLOR, S. A.

FABRICA: Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid) Fax ventas: 91 884 43 39 e-mail: landecolor@landecolor.com web: www.landecolor.es









DATA SHEET 1/3

SYNTHETIC CHLORINATED-RUBBER ENAMEL (Swimming-pool chlorinated rubber paint)

Fast-drying synthetic chlorinated rubber-based enamel, great adhesion, outstanding chemical resistance to acids and alkalis, and great resistance to sea water and sea environments.

PRODUCT DATA

> Specific gravity: 1.400 <u>+</u> 0.05 g/cm³ @ 20°C

Viscosity: 80 <u>+</u> 10 KU at 20°C

> Finish: Satin

> Normal thickness of film: From 25 to 30 microns

➤ Air dry times (20°C):

Dry to touch: 20 minutes Dry without stickiness: 30 minutes Totally dry: 2 hours

> Recoat time: At least 24 hours air dry

Grinding Fineness: 40 microns

COVERAGE

9-10 m²/kg, depending on surface conditions.

PACKING

Available in 4 and 15 ltr cans.

USES

Due to its excellent properties, swimming-pool chlorinated-rubber paints is suitable for protecting both interior and exterior surfaces exposed to weather and aggressive chemicals. In addition, this product is highly resistant to drinking and sea water. It may also be used to **put up directions in car parks**, factories, etc. Do not apply at temperatures below 5 ° C or above 35 ° C.



LANDECOLOR, S. A.

FABRICA: Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid) Fax ventas: 91 884 43 39 e-mail: landecolor@landecolor.com web: www.landecolor.es











DATA SHEET 2/3

SYNTHETIC CHLORINATED-RUBBER ENAMEL (Swimming-pool chlorinated rubber paint)

SURFACES

The surfaces to be coated must be clean, consistent, and totally free of grease.

Surfaces should be prepared by applying a coat of chlorinated-rubber primer or quick-drying synthetic coating.

If applied on **old paint**, apply directly after washing and matt sanding.

Please strip surfaces in a bad condition.

INSTRUCTIONS FOR USE

Please stir the product before use for the content of the container to reach full homogeneity.

The product may be applied using a spray gun, brush or a roller:

> Spray gun: Thin paint using our Fast Solvent for chlorinated rubber paints until the adequate level of viscosity has been reached.

Application conditions:

Pressure: 3 to 4 atm.

1 / 1.5 / 2 mm. Nozzle:

Coats: One light coat.

> Roller and brush: Apply a first coat thinned with 5% Fast Solvent for chlorinated rubber paints, and a second coat as supplied.

Tools must be cleaned with Fast Solvent for chlorinated rubber paints.



LANDECOLOR, S. A.

FABRICA: Polígono Industrial n.º 1











DATA SHEET 3/3

SYNTHETIC CHLORINATED-RUBBER ENAMEL (Swimming-pool chlorinated rubber paint)

COLOURS

White, swimming-pool blue and black.

STORAGE

Up to 24 months in original unopened container.

Please keep away from freezing temperatures and direct exposure to sunlight.

••••••

We guarantee the quality of our products in accordance with our general conditions of sales and supply. Our technical recommendations of usage, expressed verbally, in written form, or by means of tests, are offered to the best of our knowledge and current experience. They constitute simple indications which do not intend any liability on our part nor do they exempt customers from their need to check by themselves that the products supplied by us match their required procedures and goals by conducting their own monitoring checks and tests.

The application and usage of these products are outside our control. Consequently, customers exclusively shall be liable for these. We accept no liability for any results other than the ones shown here. Our safety recommendations shall not prevent customers from determining their own amounts subject to the conditions of their premises. We reserve the right to change the data in this sheet without prior notice as data evolve technologically.