



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



## DATA SHEET

1/3

### CHLORINATED-RUBBER ALKYD PRIMER

Anti-corrosive modified chlorinated-rubber primer suitable for protecting metal structures in highly aggressive industrial and marine environments.

#### PRODUCT DATA

- |                             |                                       |
|-----------------------------|---------------------------------------|
| ➤ Specific gravity:         | 1.600± 0.050 g/cm <sup>3</sup> @ 20°C |
| ➤ Viscosity:                | 110 ± 5 KU at 20°C                    |
| ➤ Finish:                   | matt                                  |
| ➤ Normal thickness of film: | from 40 to 50 microns                 |
| ➤ Air dry times (20°C):     |                                       |
| Dry to touch:               | 15-20 minutes                         |
| Totally dry:                | 2 hours                               |
| ➤ Recoat time:              | 12 hours                              |
| ➤ Flash point               | 35° C                                 |

#### COVERAGE

6-7 m<sup>2</sup>/kg, depending on surface conditions.

#### PACKING

Available in 15 ltr cans.

#### USES

Anti-corrosion primer to be used for **agricultural and industrial machinery**.  
Apply this product as a first anti-corrosive coat under chlorinated-rubber alkyd enamel (special product outside rate scheme).

The use of an **inadequate solvent** will create paint adhesion problems.



# LANDECOLOR, S. A.

FABRICA: Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



## DATA SHEET

2/3

### CHLORINATED-RUBBER ALKYD PRIMER

#### SURFACES

If applied on steel, it is recommended to clean the surface using abrasive blasting Sa2. Good cleaning using a wire brush may also be possible.

On already painted surfaces, remove all traces of loose paint, dust, and grease.

#### INSTRUCTIONS FOR USE

Please stir the product before use for the content of the container to reach full homogeneity.

The product may be applied using a spray gun, brush or a roller:

- **Spray gun:** Apply a first coat thinned with 10-20% fast solvent for synthetics and chlorinated rubbers until the adequate level of viscosity has been reached (30" CF4).

Application conditions:	Pressure:	3 to 4 atm.
	Nozzle:	1 / 1.5 / 2 mm.
	Coats:	one light coat.

- **Roller and brush:** Apply a first coat thinned with 10% fast solvent for synthetics and chlorinated rubbers, and a second coat as supplied.

Tools must be cleaned with fast solvent for synthetics and chlorinated rubbers.



**LANDECOLOR, S. A.**

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



## DATA SHEET

3/3

### CHLORINATED-RUBBER ALKYD PRIMER

#### COLOURS

Grey and red iron oxide.

#### STORAGE

Up to 24 months in original unopened container.

Please keep away from freezing temperatures and direct exposure to sunlight.



We guarantee the quality of our products in accordance with our general conditions of sales and supply. Our technical recommendations of usage, expressed verbally, in written form, or by means of tests, are offered to the best of our knowledge and current experience. They constitute simple indications which do not intend any liability on our part nor do they exempt customers from their need to check by themselves that the products supplied by us match their required procedures and goals by conducting their own monitoring checks and tests.

The application and usage of these products are outside our control. Consequently, customers exclusively shall be liable for these. We accept no liability for any results other than the ones shown here. Our safety recommendations shall not prevent customers from determining their own amounts subject to the conditions of their premises. We reserve the right to change the data in this sheet without prior notice as data evolve technologically.

Issued on 30 Jun. 11. This DATA SHEET supersedes all previous