



LANDECOLOR, S. A.

FABRICA: Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



## DATA SHEET

1/2

### 1-COMPONENT COLOURLESS NITROCELLULOSE LACQUER

Transparent nitrocellulose varnish, quick to dry, excellent hardness, and soft touch, suitable for decorative finishing of all kinds of woods used indoors.

#### PRODUCT DATA

- *Specific gravity:* 0,940 ± 0.05 g/cm<sup>3</sup> @ 20°C
- *Viscosity:* 25 + 5 CF4 at 20°C
- *Recoat time:* 24 hours
- *Finish:* Gloss, satin and matt
- *Air dry times (20°C):*
  - Dry to touch:* 10-15 minutes
  - Dry without stickiness:* 25-30 minutes
  - Totally dry:* 1 hour

#### COVERAGE

**12-16 m<sup>2</sup>/lt**, depending on surface conditions.

#### PACKING

Available in 0.750 and 4 ltr cans.

#### USES

Recommended for interior **doors, furniture, and windows**. Suitable for **DIY projects, cabinetmaking, carpentry, and restoration of old furniture**.

#### SURFACES

Surfaces must be clean, in sound condition, and free of grease and easily breakable substances.



LANDECOLOR, S. A.

FABRICA: Polígono Industrial n.º 1

C/. Soria, 38 - Telef. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



## DATA SHEET

2/2

# 1-COMPONENT COLOURLESS NITROCELLULOSE LACQUER

## INSTRUCTIONS FOR USE

Remove content from the container.

Apply using a **brush, roller, or spray gun**. Thin paint using our general-use nitro solvent until the adequate level of viscosity has been reached.

Application conditions:	Pressure:	3 to 4 atm.
	Nozzle:	1 / 1.5 / 2 mm.
	Coats:	one light coat.

Tools must be cleaned with general-use nitro solvent.

## STORAGE

Up to 24 months in original unopened container.

Please keep away from freezing temperatures and direct exposure to sunlight.



We guarantee the quality of our products in accordance with our general conditions of sales and supply. Our technical recommendations of usage, expressed verbally, in written form, or by means of tests, are offered to the best of our knowledge and current experience. They constitute simple indications which do not intend any liability on our part nor do they exempt customers from their need to check by themselves that the products supplied by us match their required procedures and goals by conducting their own monitoring checks and tests.

The application and usage of these products are outside our control. Consequently, customers exclusively shall be liable for these. We accept no liability for any results other than the ones shown here. Our safety recommendations shall not prevent customers from determining their own amounts subject to the conditions of their premises. We reserve the right to change the data in this sheet without prior notice as data evolve technologically.