



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

1/2

MATT POLITEX P-300

This copolymer-based water-dispersed plastic paint is especially designed for protecting and decorating all kinds of buildings.

APPROVED.

PRODUCT DATA

- *Specific gravity:* 1.650 ± 0.05 g/cm³ @ 20°C
- *Viscosity:* 120 + 5 KU at 20°C
- *Finish:* Matt.
- *Air dry times (20°C):*
 - Dry to touch:* 20 minutes
 - Totally dry:* 2 hours
- *Recoat time:* 6 hours
- *Washability test:* At least 6.000 cycles.

COVERAGE

5-6 m²/kg, depending on surface conditions.

PACKING

Available in 4, 8 and 15 ltr cans.

USES

For interior and exterior use.

Since this is a plastic paint, it is fire-resistant (M-1).

This product is designed for protecting and decorating **façades, walls, cafeterias, flights of stairs, ceilings, business premises, etc.**

It is easy to apply, dries fast, features good washability properties and high resistance to weather.



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

2/2

MATT POLITEX P-300

SURFACES

Surfaces must be clean, in sound condition, and free of grease and easily breakable substances.

INSTRUCTIONS FOR USE

Please stir the product before use for the content of the container to reach full homogeneity.

The product may be applied using a spray gun, brush or a roller, thinning paint using water until the adequate level of viscosity has been reached (10% apr).

Tools must be cleaned with water.

COLOURS

White.

STORAGE

Up to 24 months in original unopened container.

Please keep away from freezing temperatures and direct exposure to sunlight.



We guarantee the quality of our products in accordance with our general conditions of sales and supply. Our technical recommendations of usage, expressed verbally, in written form, or by means of tests, are offered to the best of our knowledge and current experience. They constitute simple indications which do not intend any liability on our part nor do they exempt customers from their need to check by themselves that the products supplied by us match their required procedures and goals by conducting their own monitoring checks and tests.

The application and usage of these products are outside our control. Consequently, customers exclusively shall be liable for these. We accept no liability for any results other than the ones shown here. Our safety recommendations shall not prevent customers from determining their own amounts subject to the conditions of their premises. We reserve the right to change the data in this sheet without prior notice as data evolve technologically.