



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

1/3

ROCHALACK LACQUER WITH POLYURETHANE

Single-component polyurethane lacquer enamel designed to achieve highly hard finishes. It is suitable for marine, industry, and decoration uses. For interior and exterior use.

PRODUCT DATA

- | | |
|-----------------------------|---------------------------------------|
| ➤ Specific gravity: | 1.200 + 0.05 g/cm ³ @ 20°C |
| ➤ Viscosity: | 90 + 10 KU at 20°C |
| ➤ Finish: | gloss and satin |
| ➤ Normal thickness of film: | from 25 to 30 microns |
| ➤ Air dry times (20°C): | |
| Dry to touch: | 1 hour |
| Dry without stickiness: | 3 hours |
| Totally dry: | 8 hours |
| ➤ Recoat time: | 8-12 hours |
| ➤ Grinding Fineness: | 10 – 15 microns |

COVERAGE

8-12 m²/kg, depending on surface conditions.

PACKING

Available in 0.750, and 4 ltr cans.

USES

This product is very suitable for decorating **furniture, iron, shelves, bathrooms, kitchens, etc.** It is resistant to chemicals, detergents, soaps, oils, etc.

Do not apply at temperatures below 5 ° C or above 35 ° C.



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Telef. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

2/3

ROCHALACK LACQUER WITH POLYURETHANE

SURFACES

The surfaces to be coated must be clean, consistent, and totally free of grease.

If applied on unvarnished **wood**, please apply a first coat of our matt sealer or our nitro base primer and let it dry, sand it afterwards, and remove all remaining dust.

If applied on **iron**, please prime the surface with our Electrolytic Red Lead or our synthetic primers.

If applied on **old paint**, apply directly after washing and matt sanding.

Please strip surfaces in a bad condition.

INSTRUCTIONS FOR USE

Please stir the product before use for the content of the container to reach full homogeneity.

The product may be applied using a spray gun, brush or a roller:

- **Spray gun:** Thin paint using our Slow Solvent for Synthetics or turpentine until the adequate level of viscosity has been reached.
Application conditions: Pressure: 3 to 4 atm.
 Nozzle: 1 / 1.5 / 2 mm.
 Coats: one light coat.
- **Roller or brush:** Apply a first coat thinned with 10% Slow Solvent for Synthetics or turpentine, and a second coat as supplied.

Tools must be cleaned with Slow Solvent for Synthetics or turpentine.



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

3/3

ROCHALACK LACQUER WITH POLYURETHANE

COLOURS

White gloss.

White, black and others satin.

STORAGE

Up to 24 months in original unopened container.

Please keep away from freezing temperatures and direct exposure to sunlight.



We guarantee the quality of our products in accordance with our general conditions of sales and supply. Our technical recommendations of usage, expressed verbally, in written form, or by means of tests, are offered to the best of our knowledge and current experience. They constitute simple indications which do not intend any liability on our part nor do they exempt customers from their need to check by themselves that the products supplied by us match their required procedures and goals by conducting their own monitoring checks and tests.

The application and usage of these products are outside our control. Consequently, customers exclusively shall be liable for these. We accept no liability for any results other than the ones shown here. Our safety recommendations shall not prevent customers from determining their own amounts subject to the conditions of their premises. We reserve the right to change the data in this sheet without prior notice as data evolve technologically.

Issued on 30 Jun. 11. This DATA SHEET supersedes all previous.