



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

1/2

BINDER FOR PARKS AND GARDENS

Aqueous dispersion to bind gravel together providing very good adhesion properties, drainage and mottled appearance of the film. It enhances the natural beauty of stone.

Excellent outdoor resistance and very quick to dry.

PRODUCT DATA

- | | |
|-------------------------|--|
| ➤ Specific gravity: | 1.020 \pm 0.050 g/cm ³ @ 20°C |
| ➤ Viscosity: | 20 \pm 5" CF4 at 20°C |
| ➤ Non volatile content: | 40 \pm 1 % |
| ➤ finish: | Colour-less semi-mattt. |
| ➤ Air dry times (20°C): | |
| Dry to touch: | 40 minutes |
| Totally dry: | 24 hours |

COVERAGE

Depending on surface conditions (see instructions for use)

PACKING

Available in 5 and 25 ltr cans.

USES

Outstanding solution for surface binding or as mass binder of crushed marble or other types of aggregates usually used in roundabouts, gardening decoration, etc. or in places with limited passage of people.

Easy to apply, great hardness and washability.



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

2/2

BINDER FOR PARKS AND GARDENS

INSTRUCTIONS FOR USE

Stir the product before use for the content of the container to reach full homogeneity.

- If the application depends on the binding degree of the aggregates, we recommend, as a guideline, the following dosages:

<u>Granulometry</u>	<u>Dosage</u>
1,50-2,00 cm	3,5%
1,0-1,5 cm	5%
0,7-1,0 cm	7%

- If the application is made by surface spraying, consumption will be determined by granulometry. As a guideline, this consumption will be comprised between 800 and 1,200 g/m², for a thickness of the aggregates' layer of 3-5 cm. A 1:10 dilution in water is recommended for this kind of application.

STORAGE

Up to 24 months in original unopened container.

Please keep away from freezing temperatures and direct exposure to sunlight.



We guarantee the quality of our products in accordance with our general conditions of sales and supply. Our technical recommendations of usage, expressed verbally, in written form, or by means of tests, are offered to the best of our knowledge and current experience. They constitute simple indications which do not intend any liability on our part nor do they exempt customers from their need to check by themselves that the products supplied by us match their required procedures and goals by conducting their own monitoring checks and tests.

The application and usage of these products are outside our control. Consequently, customers exclusively shall be liable for these. We accept no liability for any results other than the ones shown here. Our safety recommendations shall not prevent customers from determining their own amounts subject to the conditions of their premises. We reserve the right to change the data in this sheet without prior notice as data evolve technologically.