



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

1/3

TAR EPOXY BLACK PAINT INTA 164407

**Protective paint for steel and cement in corrosive environments.
APPROVED.**

PRODUCT DATA

- | | |
|------------------------------------|---------------------------------------|
| ➤ <i>Specific gravity:</i> | 1.290 ± 0.05 g/cm ³ @ 20°C |
| ➤ <i>Viscosity:</i> | 115 ± 5 KU at 20°C |
| ➤ <i>Finish:</i> | Black. |
| ➤ <i>Normal thickness of film:</i> | 100 Microns |
| ➤ <i>Recoat time:</i> | 24 hours |
| ➤ <i>Curing time:</i> | 7 days |

COVERAGE

4-5 m²/kg, depending on surface conditions.

SUPPLY AND MIXING RATIO

This is a two-component product presented in two separate containers (base and catalyst).

- | | |
|------------------------|--------------------------|
| ➤ <i>Mixing ratio:</i> | |
| <i>Base:</i> | 20 part in volume. |
| <i>Catalyst:</i> | 1 part in volume. |
| ➤ <i>Mix life:</i> | 8-10 hours. |
| ➤ <i>Supplied in:</i> | 20 Kg. metal containers. |



LANDECOLOR, S. A.

FABRICA: Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

2/3

TAR EPOXY BLACK PAINT INTA 164407

USES

Suitable to protect **metal surfaces under continuous or alternate immersion in fresh or salted water, highly corrosive atmospheres, marine environments, and attacks by aggressive alkaline and moderately acid chemicals.** Also recommended to protect **buried steel surfaces.**

It can be used to paint the interior of deposits, oil transports, and salted water ballasts.

Very good results are obtained in the **protection of cement surfaces, residual water industries, paper factories, and chemical industries.**

SURFACES

Abrasive blasting Sae 2 1/2. Concrete surfaces must be clean and dry, making them rough through acid attack or blasting.

INSTRUCTIONS FOR USE

Please stir the product before use for the content of the container to reach full homogeneity. 15 minutes pass before its use.

The product may be applied using a spray gun, roller or brush.

Tools must be cleaned with Solvent for Epoxi



LANDECOLOR, S. A.

FABRICA : Polígono Industrial n.º 1

C/. Soria, 38 - Teléf. 91.884 33 59 - Fax 91.884 40 71 - 28864 AJALVIR (Madrid)

Fax ventas: 91 884 43 39

e-mail: landecolor@landecolor.com

web: www.landecolor.es



DATA SHEET

3/3

TAR EPOXY BLACK PAINT INTA 164407

COLOURS

Black

STORAGE

Up to 24 months in original unopened container.

Please keep away from freezing temperatures and direct exposure to sunlight.



We guarantee the quality of our products in accordance with our general conditions of sales and supply. Our technical recommendations of usage, expressed verbally, in written form, or by means of tests, are offered to the best of our knowledge and current experience. They constitute simple indications which do not intend any liability on our part nor do they exempt customers from their need to check by themselves that the products supplied by us match their required procedures and goals by conducting their own monitoring checks and tests.

The application and usage of these products are outside our control. Consequently, customers exclusively shall be liable for these. We accept no liability for any results other than the ones shown here. Our safety recommendations shall not prevent customers from determining their own amounts subject to the conditions of their premises. We reserve the right to change the data in this sheet without prior notice as data evolve technologically.